

FLAT SNOW 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A037250 | 5X20 | 8,20 | REVESTI |



| DIMENSIONS AND SURFACE PROPERTIES | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

| PHYSICAL PROPERTIES | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

| CHEMICAL PROPERTIES | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

THREE-D SNOW 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037242 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

CUPS SNOW 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037230 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

PYRAMID SNOW 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037234 | 5X20 | 11,50 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

FLAT GREY 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A037251 | 5X20 | 8,30 | REVESTI |

| DIMENSIONS AND SURFACE PROPERTIES | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |

| PHYSICAL PROPERTIES | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

| CHEMICAL PROPERTIES | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

THREE-D GREY 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037243 | 5X20 | 11,60 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

CUPS GREY 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037231 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

PYRAMID GREY 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037235 | 5X20 | 11,50 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

FLAT PALLADIUM 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037370 | 5X20 | 8,00 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

THREE-D PALLADIUM 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037368 | 5X20 | 10,90 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

CUPS PALLADIUM 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037365 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

PYRAMID PALLADIUM 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037366 | 5X20 | 11,50 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

FLAT BLUE 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037253 | 5X20 | 7,80 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

THREE-D BLUE 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037245 | 5X20 | 11,60 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

CUPS BLUE 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037233 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES


| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

PYRAMID BLUE 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037237 | 5X20 | 11,50 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

FLAT TERRACOTA 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|-----------|-----------|----------------|---------|
| A037656 | 5X20 | 7,80 | REVESTI |

DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

THREE-D TERRACOTA 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037655 | 5X20 | 10,90 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES


| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

CUPS TERRACOTA 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037653 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES


| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

PYRAMID TERRACOTA 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037654 | 5X20 | 11,50 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES


| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

FLAT NIGHT 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037252 | 5X20 | 7,80 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

THREE-D NIGHT 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037244 | 5X20 | 11,60 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES


| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

CUPS NIGHT 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037232 | 5X20 | 11,20 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |

PYRAMID NIGHT 5X20

| REFERENCE | SIZE (cm) | THICKNESS (mm) | GROUP |
|----------------|-----------|----------------|---------|
| A037236 | 5X20 | 11,50 | REVESTI |



DIMENSIONS AND SURFACE PROPERTIES

| | | |
|---|--------------|----------------------------------|
| Size, thickness, side straightness, flatness, orthogonality | UNE-EN 14411 | It accomplished all requeriments |
|---|--------------|----------------------------------|

PHYSICAL PROPERTIES

| | | |
|---------------------------|-----------------|------------------------|
| Water absorption capacity | EN ISO 10545-03 | >10% |
| Flexion resistance | EN ISO 10545-04 | => 20N/mm ² |
| Thermal shock resistance | EN ISO 10545-09 | It stands the test |
| Frost resistance | EN ISO 10545-12 | Not pass the test |

CHEMICAL PROPERTIES

| | | |
|--|-----------------|------|
| Resistance to cleaning products | EN ISO 10545-13 | GLA |
| Resistance to chemical products in swimming pool water | EN ISO 10545-13 | 0.00 |
| Stains resistance | EN ISO 10545-14 | 5 |